

Micro-structures and magnetic properties of Mg-Al substituted in barium hexa-ferrite prepared by co-precipitation method

Martha Rianna¹, Timbangan Sembiring^{1*}, Marhaposan Situmorang¹, Anggito P. Tetuko², Eko Arief Setiadi¹, Masno Ginting², Perdamean Sebayang²

¹Department of Physics, Universitas Sumatera Utara, Medan 20155, Indonesia

²Research Center for Physics, Indonesian Institute of Sciences (LIPI), Tangerang Selatan, Banten 15314, Indonesia

*timbangan@usu.ac.id

Abstract. In this study, Mg-Al substituted barium hexa-ferrite of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ ($x=0-0.2$) materials using co-precipitation method at a calcination temperature of 1200°C for 2 hours were carried out. The precursor concentrations of the mixture were varied to identify the optimum sample. The final powder was characterized by using XRD, FE-SEM, and VSM. The XRD shows that the Mg-Al substitution was not change the micro-structures of barium hexa-ferrite. FE-SEM observation was carried out on the surface of hexagonal shape of barium hexa-ferrite. The magnetic properties shows that the decreases saturation (M_s), remanence (M_r) and coercivity (H_c). The optimum condition was obtained on $x=0.2$ with $M_s= 29.28$ emu/g, $M_r= 15.33$ emu/g, $H_c= 1259$ Oe.

1. Introduction

Barium hexa-ferrite ($\text{BaFe}_{12}\text{O}_{19}$) is one of hard magnetic materials with high magnetic saturation and coercivity, excellent corrosion resistance and chemical stability [1–4]. Many reports are available for the synthesis and characterization of the barium hexaferrite substituted with various cations such as: Mn, Al, Mg, Co, Ni, Ti, Zn for Fe [5-12].

Previous study on the barium hexa-ferrite doped Al and Mn (0.12, 0.24; and 0.42 wt%) sintered at 1000 and 1100 °C for 2 hours [13]. The results suggested that show decrease of the magnetic flux, saturation, and remanence values as the additive concentration increases. Shaayan et al. [14], reported that the synthesis of $\text{BaFe}_{12-x}\text{Al}_x\text{O}_{19}$ at a calcination temperature of 1100 °C for 9 h using a mechanical alloying method, resulted that the decrease of the saturation magnetization in addition of Al. Kumar et al. [15] reported that the synthesis of $\text{BaMg}_x\text{Fe}_{(12-x)}\text{O}_{19}$ using the sol gel method with calcination temperature at 1100°C for 2 hours. The results confirmed that, Mg has been substitution in $\text{BaFe}_{12}\text{O}_{19}$ with single phase hexagonal structure.

In this study, Mg-Al substituted barium hexa-ferrite of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ ($x=0-0.2$) materials using co-precipitation method at a calcination temperature of 1200°C for 2 hours were carried out.

2. Experimental Method

Barium hexa-ferrite with doping materials of Mg-Al ($x=0-0.2$) were synthesized using a co-precipitation method where barium chloride (BaCl_2), iron chloride (FeCl_3), magnesium chloride (MgCl_2), and aluminium chloride (AlCl_3) were used as the raw materials. The materials were dissolved in 25 ml of HCl (37%) and magnetically stirred for 30 minutes at room temperature. The solution was then mixed with aquadest of 50 ml in a beaker glass and

was stirred using a magnetic stirrer at 500 rpm until homogeneous solution is obtained. The solution was washed 10 times using distilled water until a neutral pH of 7 is obtained and was dried in the oven for 15 hours at a temperature of 100 °C. Then, the powder was calcinated at a temperature of 1200°C for 2 hours and at a heating rate of 10 °C/minutes.

The final powder of barium hexa-ferrite material were analysed using X-ray Diffraction (Rigaku Smartlab), Field Emission Scanning Electron Microscopy (JEOL), Vibrating Sample Magnetometer (VSM250 Deking Magnet Ltd).

3. Result and Discussion

Figure 1 shows the XRD pattern of Mg-Al substituted barium hexa-ferrite calcinated at a temperature of 1200°C. The samples with substituted of Mg-Al have single phase of $\text{BaFe}_{12}\text{O}_{19}$ with hexagonal crystal structure. In addition, the additive is likely occur as the ions, where Mg-Al ions replace Fe ions [16].




Figure 1. The XRD Patterns: $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ powder samples ($x=0-0.2$)

Figure 2 shows that the FE-SEM images of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ powder samples ($x=0-0.2$) prepared by co-precipitation method after temperature calcination at 1200°C for 2 hours in the air atmosphere. From Figures 2 for all FE-SEM images, it can be seen that the particle inside the sample was grown with relatively uniform shape. The particles were nearly hexagonal shape with average 5 μm .




Figure 2.FE-SEM image of BaFe_{12-2x}Mg_xAl_xO₁₉ (a) x=0 (b) x=0.2




Figure 3.Hysteresis Curve of BaFe_{12-2x}Mg_xAl_xO₁₉ Powder (x= 0-0.2)

Table 1.Magnetic Properties of BaFe_{12-2x}Mg_xAl_xO₁₉ (x=0-0.2)

Sample	Magnetic Properties		
	Ms (emu g ⁻¹)	Mr (emu g ⁻¹)	Hc (Oe)
0	38.42	20.39	1736
0.1	34.25	18.07	2576
0.2	29.28	15.33	1259

Figure 3 represents that the hysteresis curves of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ ($x=0-0.2$). The characteristic magnetic parameters of $\text{BaFe}_{12-2x}\text{Co}_x\text{Ni}_x\text{O}_{19}$ ($x=0-0.2$) are listed in Table 1. It can be seen that the substitution of the Mg-Al ions caused decrease the values of Saturation (M_s), Remanent (M_r), Coercivity (H_c). The decreases in magnetic parameters were due to the net alignment of grain magnetization. Considering the above results, Mg and Al have paramagnetic of magnetic properties, then Fe is ferromagnetic [16].

4. Conclusion

Mg-Al substituted barium hexa-ferrite of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ ($x=0-0.2$) materials using co-precipitation method at a calcination temperature of 1200°C for 2 hours were carried out. The XRD shows that the Mg-Al substitution was not change the micro-structures of barium hexa-ferrite. FE-SEM observation was carried out on the surface of hexagonal shape of barium hexa-ferrite. The magnetic properties shows that the decreases saturation (M_s), remanence (M_r) and coercivity (H_c). The optimum condition was obtained on $x=0.2$ with $M_s= 29.28$ emu/g, $M_r= 15.33$ emu/g, $H_c= 1259$ Oe, and is suitable as an absorber of micro-wave material.

References

- [1] Y. Y. Meng *et al.*, "Synthesis of barium ferrite ultrafine powders by a sol-gel combustion method using glycine gels," *J. Alloys Compd.*, vol. 583, pp. 220–225, 2014.
- [2] S. Budiawanti, B. Soegijono, and I. Mudzakir, "Influence of calcinations on structural and magnetic properties of $\text{BaFe}_{12}\text{O}_{19}$ thin films prepared by chemical solution deposition," in *AIP Conference Proceedings*, 2018, vol. 2023.
- [3] Y. Lin, Y. Liu, J. Dai, L. Wang, and H. Yang, "Synthesis and microwave absorption properties of plate-like $\text{BaFe}_{12}\text{O}_{19}/\text{Fe}_3\text{O}_4$ core-shell composite," *J. Alloys Compd.*, vol. 739, pp. 202–210, 2018.
- [4] L. H. Shao, S. Y. Shen, H. Zheng, P. Zheng, Q. Wu, and L. Zheng, "Effect of Powder Grain Size on Microstructure and Magnetic Properties of Hexagonal Barium Ferrite Ceramic," *J. Electron. Mater.*, vol. 47, no. 7, pp. 4085–4089, 2018.
- [5] V. V. Soman, V. M. Nanoti, and D. K. Kulkarni, "Dielectric and magnetic properties of Mg-Ti substituted barium hexaferrite," *Ceram. Int.*, vol. 39, no. 5, pp. 5713–5723, 2013.
- [6] T. Ben Ghzaïel, W. Dhaoui, F. Schoenstein, P. Talbot, and F. Mazaleyrat, "Substitution effect of $\text{Me} = \text{Al}, \text{Bi}, \text{Cr}$ and Mn to the microwave properties of polyaniline/ $\text{BaMeFe}_{11}\text{O}_{19}$ for absorbing electromagnetic waves," *J. Alloys Compd.*, vol. 692, pp. 774–786, 2017.
- [7] S. Singhal, K. Kaur, S. Jauhar, S. Bhukal, and S. Bansal, "Structural and Magnetic Properties of $\text{BaCo}_x\text{Fe}_{12-x}\text{O}_{19}$ ($x = 0.2, 0.4, 0.6, \& 1.0$) Nanoferrites Synthesized Via Citrate Sol-Gel Method," *World J. Condens. Matter Phys.*, vol. 1, no. 3, pp. 101–104, 2011.
- [8] A. Y. Sari, C. H. Safira, E. A. Setiadi, S. Simbolon, C. Kurniawan, and P. Sebayang, "EFEK ADITIF FeMo DAN PROSES KALSINASI PADA SERBUK MAGNETIK $\text{BaFe}_{12}\text{O}_{19}$," *J. Sains Mater. Indones.*, vol. 18, no. 3, p. 95, 2018.
- [9] P. Sebayang, A. Y. Sari, D. Ginting, Y. Allan, M. N. Nasruddin, and K. Sebayang, "Characteristics of B_2O_3 and Fe added into $\text{BaFe}_{12}\text{O}_{19}$ permanent magnets prepared at different milling time and sintering temperature," in *AIP Conference Proceedings*,

- 2016, vol. 1711.
- [10] M. Rianna *et al.*, “Microstructure and magnetic properties of $\text{BaFe}_{12-2x}\text{Mg}_x\text{Al}_x\text{O}_{19}$ for microwave absorbing materials,” *Int. J. Appl. Eng. Res.*, vol. 12, no. 17, pp. 6586–6590, 2017.
 - [11] G. Mendoza-Suárez, L. P. Rivas-Vázquez, J. C. Corral-Huacuz, A. F. Fuentes, and J. I. Escalante-García, “Magnetic properties and microstructure of $\text{BaFe}_{11.6-2x}\text{Ti}_x\text{M}_x\text{O}_{19}$ (M = Co, Zn, Sn) compounds,” *Phys. B Condens. Matter*, vol. 339, no. 2–3, 2003.
 - [12] V. S. Salvi and V. H. Joshi, “Effect of dopants on barium hexaferrite,” *Indian J. Pure Appl. Phys.*, vol. 47, no. 4, pp. 277–281, 2009.
 - [13] E. A. Setiadi, C. Kurniawan, P. Sebayang, and M. Ginting, “Microstructures, physical and magnetic properties of $\text{BaFe}_{12}\text{O}_{19}$ permanent magnets with the addition of Al_2O_3 - MnO ,” *J. Phys. Conf. Ser.*, vol. 817, p. 12054, 2017.
 - [14] A. Shayan, M. Abdellahi, F. Shahmohammadian, S. Jabbarzare, A. Khandan, and H. Ghayour, “Mechanochemically aided sintering process for the synthesis of barium ferrite: Effect of aluminum substitution on microstructure, magnetic properties and microwave absorption,” *J. Alloys Compd.*, vol. 708, pp. 538–546, 2017.
 - [15] A. Kumar, V. Agarwala, and D. Singh, “Effect of Mg Substitution on Microwave Absorption of $\text{BaFe}_{12}\text{O}_{19}$,” *Adv. Mater. Res.*, vol. 585, pp. 62–66, 2012.
 - [16] M. Rianna *et al.*, “Effect of calcination temperature on Microstructures, magnetic properties, and microwave absorption on $\text{BaFe}_{11.6}\text{Mg}_{0.2}\text{Al}_{0.2}\text{O}_{19}$ synthesized from natural iron sand,” *Case Stud. Therm. Eng.*, vol. 13, 2019.